

High Performance Packings

STYLE
154
FDA




PTFE packing, interlock braid with a break-in lubricant.
Food Grade FDA PTFE filaments and break-in lubricant.

Interlock Braid Construction

Temp: To 500° F (260° C) pH: 0 - 14
Pressure: To 300 psi* Speed: 1500 FPM
*pump service

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	72	31	19.4	12.5	9	7	5.1	4.1	3.3	2.3	1.7	1.2

STYLE
165



Graphite filled PTFE fibre packing that improves thermal conductivity and will not harden. Commonly called GFO®

Interlock Braid Construction

Temp: To 550° F (285° C) pH: 0 - 14
Pressure: To 300 psi Speed: 4300 FPM

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	69	36	21	14	10	7	5.7	4.5	3.5	2.5	1.9	1.5

STYLE
170



Aramid fibre packing with an inert lubricant. Extremely durable, highly abrasive resistant packing. Ideal for slurry service.

Interlock Braid Construction

Temp: To 500° F (260° C) pH: 3 - 11
Pressure: To 500 psi Speed: 1900 FPM

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	78	37	22	16.5	11.4	8	6	4.9	3.6	2.6	2.3	1.6

STYLE
528



Flax fibre packing, lubricated with tallow and wax. Used for brine, cold water and oil service. Ideal for marine applications.

Square Braid Construction

Temp: To 200° F (105° C) pH: 5 - 9
Pressure: To 150 psi Speed: 1200 FPM

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	139	59	28	21	14.8	10.7	8.6	6.5	5.1	3.6	2.8	2.3

STYLE
1152




Special syntex fibre, each strand impregnated with PTFE dispersion both prior to and after braiding. Finished packing also has a break-in lubricant. An asbestos replacement packing for general service applications. Good chemical resistance.

Interlock Braid Construction

Temp: To 500° F (260° C) pH: 0 - 12
Pressure: To 500 psi Speed: 2200 FPM

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	88	48	25	16.6	12	8.5	6.4	5.7	4.2	2.9	2.6	1.7

STYLE
1398



Syntex fibre packing impregnated with a high temperature lubricant. Finished packing is surface graphited. An asbestos replacement packing for general service use on pumps and valves.

Interlock Braid Construction

Temp: To 500° F (260° C) pH: 4 - 10
Pressure: To 300 psi Speed: 1500 FPM

In.	1/8	3/16	1/4	5/16	3/8	7/16	1/2	9/16	5/8	3/4	7/8	1
Ft./lb.	128	56	31	21	16	11	8.6	6.7	5.8	4	3	2.1

861 Cranberry Court
Oakville, ON L6L 6J7

Phone: (905) 847-6500
Fax: (905) 847-6943
email: sales@daemarinc.com

www.daemar.com

SUPPLYING
THE PACE OF INDUSTRY
1-800-387-7115





Braided Packing Interchange

DMR™	Albion	Anchor	Chesterton	Crane	Garlock	JM	RM	Sepco
1-T		1320	1729		740		524	ML-1
49		399	420	550	344	280		
50		CARPACK	1738	1655-CF	5000	C-44	864	ML-4461
90	183	3400	370-477-1	1650-CF	98, 88	5319, C45, C19	861, 862	ML-4460
154	167,169	1121	1724,324	C-1045	5888, PM-7	VX-1, VX-2	847	ML-2254
152S		1120	328, 1728	C-1050	5889, PM-8	CX-1	849	ML-2235
154FDA		1165	1725	715, 1055	5900		848-FDA	ML-2236FDA
156		1123-B.T.	382	C-1050-M	620		846	2210
160	182	1342	1, 375	1625-G	200	C1 C2	863	ML-4444
165	181	1140	1750	C-1065	5100, PM-6	5320, C26	845	ML-4002
165K		5079		C-1064	6-K	C-27	844	ML-4004
170		4029	1740	1730	5200, PM-5	C-17, 5317	981	ML-4800
182		1334		1760	8904, PM-4	C-67	951	ML-6225
525T	184	TUFTEX 4040	329	867	5413		523, 528T	219
528	110, 114	NESTOR	80	863N	18	CW-2, CW-3, CW-4	522	2
531	120, 531	383, 380	81	866	90,131, 745	C-240	525	
1100-TCP		815	1400	1656, G58	1300		GRAPHA-BRAID	ML-911
1152	*160, 172, *177, 713	4039, 5039, 1500, *414, *1, *4425, *JOURNAL, *ALPULP	1710, 412-W	1335	*5862, 5861, 8922, PM-1	C-47, C-49	941	ML-2225
1152K					8921-K		945	ML-2225A
1162 IB		1173	1710 1774	1335	PM-1	C-47, C-49	941	ML-2225
1398	*175, *303, *361, *362	5017, 5019, *21, *317, *318		1340	*733, 8913, PM-2		943, 968	ML-402, ML-6402
1414	*140	750, *809	1800	387-1	*127, 127AFP, 1200PBI	333	925	ML-310
1416						G39		FG-4
1420		*1319			*117-B, 8939-B			
1430		*313			*234, 8909, PM-3		944	
3165			1760	1070	PM-6		846	ML-8002

*Products may contain asbestos. General comparisons only and should be used as "service equals" only.

